



# QuakeWrap® B26G

## Description

QuakeWrap® B26G is a high-strength biaxial glass fabric with slightly different strengths in 0° and 90° directions. The fabric is white and is impregnated in the field using QuakeBond™ 300SR Saturating Resin to form glass fiber reinforced polymer (GFRP) used to strengthen structural elements. The fabric weighs 26 oz/yd<sup>2</sup> (881 g/m<sup>2</sup>).

## Uses

- Increased live load capacity in buildings and bridges, hospital floors, roofs of buildings, etc.
- Seismic retrofit of structural elements such as columns, unreinforced masonry walls, etc.
- Repair of large diameter pipes to achieve strengthening.
- Repair of damaged structural components caused by aggressive environments, fire, vehicle impact, aging, etc.
- Changes in structural system: new openings in floors, removal of existing walls, etc.
- Correction of design or construction errors: misplaced reinforcing bars, insufficient structural depth.

## Advantages

- Strong and lightweight fabric ideal for confined spaces.
- One application adds strength in two orthogonal directions.
- Used for flexure and shear strengthening as well as confinement.
- Fully compatible and excellent adhesion to QuakeBond™ resins.
- Non-corrosive.
- Versatile; can be wrapped around complex shapes.
- Light weight does not alter mass & dynamic loads on structure.
- Special manufacturing of the fabric makes it very stable & prevents fraying.

## Coverage

40 ft<sup>2</sup> per 1-gallon (0.98 m<sup>2</sup> per 1-liter) QuakeBond™ 300SR

## Packaging

- Rolls: 50 in x 80 yards (1.27 m X 76 m).
- This fabric can be easily cut in the field to various lengths.

## Fiber & Laminate Properties

	US Units	SI Units
<b>Aerial Weight Fabric Only</b>	26 oz/yd <sup>2</sup>	881 g/m <sup>2</sup>
<b>Tensile Strength</b>	470 ksi	3.24 GPa
<b>Tensile Modulus</b>	10,500 ksi	72.4 MPa
<b>Ultimate Elongation</b>	4.5%	4.5%
<b>Density</b>	0.092 lbs/in <sup>3</sup>	2.55 g/cm <sup>3</sup>
<b>Longitudinal (0°) Direction: *</b>		
<b>Tensile Strength**</b>	64.8 ksi	447 MPa
<b>Tensile Modulus</b>	4,090 ksi	28,200 MPa
<b>Ultimate Elongation**</b>	1.44%	1.44%
<b>Breaking Force**</b>	1,420 lb/in	250 N/mm
<b>Ply Thickness***</b>	0.022 in	0.56 mm
<b>Transverse (90°) Direction: *</b>		
<b>Tensile Strength**</b>	68.3 ksi	471 MPa
<b>Tensile Modulus</b>	4,300 ksi	29,600 MPa
<b>Ultimate Elongation**</b>	1.42%	1.42%
<b>Breaking Force**</b>	1,500 lb/in.	260 N/mm
<b>Ply Thickness***</b>	0.022 in	0.56 mm

\*Results based on tests of single plies of fabrics saturated with 300SR

\*\*Mean ultimate value minus three (3) standard deviations

\*\*\*Nominal thickness of loaded fabric direction. Final laminate thickness equals 0.044 in./1.12 mm (cumulative total of ply thicknesses)

## Surface Preparation

Surface must be clean and sound; it may be dry or damp but must be free of standing water and frost. Remove dust, laitance, grease, curing compounds, disintegrated materials and other bond inhibiting materials from the surface. Existing uneven surfaces must be filled with an appropriate repair mortar. The adhesive strength of the substrate must be verified after surface preparation by random pull-off testing (ACI 503R) at the discretion of the engineer. Minimum tensile strength of 200 psi (1.4 MPa) with substrate failure is required for bond-critical applications. Blast clean, shot-blast, scarify or use other approved mechanical means to clean the substrate surface. Any sharp edges (i.e. fins, form-marks, etc.) must be ground smooth and flush. Sharp edges must be rounded to a minimum radius of 1/2 in. (19mm). Apply QuakeBond™ 220UR onto the substrate with a trowel or spatula to a normal thickness of 40 mil (1 mm). A notched trowel may be used for this application.

## The Infrastructure Innovators

QuakeWrap.com

QuakeWrap, Inc.  
6840 S. Tucson Blvd.  
Tucson, AZ 85756

Toll Free (866) QUAKEWRAP [782-5397]

QuakeWrap, Inc. warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current technical data sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. QUAKEWRAP, INC. SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES.



# QuakeWrap<sup>®</sup> B26G

## Application

Saturate QuakeWrap<sup>®</sup> B26G fabric thoroughly with QuakeBond™ 300SR; for more details refer to the Product Data Sheet for QuakeBond™ 300SR. Prior to mixing and application of QuakeBond™ 300SR, all products should be preconditioned to a temperature of 65-85°F (19-29°C). Before the epoxies harden, apply saturated fabric to the substrate surface that has been coated with QuakeBond™ 220UR. Using gloved hands, carefully remove any entrapped air bubbles under the fabric; a plastic laminating roller can be used for this purpose. If required, additional layers of saturated fabric can be directly applied on top of previous layers. Feather the edges of the fabric with QuakeBond™ 220UR.

Installation of QuakeWrap<sup>®</sup> fabrics must be performed only by specially trained and approved contractors.

Fabric can be cut to appropriate length using a commercial quality heavy-duty scissors. Since dull or worn cutting tools can damage, weaken or fray the fiber, their use should be avoided.

## Cleanup

Dispose of waste in accordance with local disposal regulation. Cured materials can only be removed mechanically. See QuakeBond™ 300SR and 220UR SDSs for more information on resin cleanup.

## Shelf Life & Storage

Shelf life is unlimited in proper storage conditions. Store in a dry environment at 45°-95°F (7°-35°C).

## Limitations

Design calculations must be made and certified by an independent licensed professional engineer. System is a vapor barrier. Concrete should not be encapsulated in areas of freeze/thaw.

## Caution

QuakeWrap<sup>®</sup> B26G is non-reactive. However, caution must be used when handling since a fine carbon dust may be present on the surface. Gloves must therefore be worn to protect against skin irritation. Caution must also be used when cutting the fabric to protect against airborne carbon dust generated by the cutting procedure. Use of an appropriate, properly fitting NIOSH approved respirator is recommended.

## First Aid

Appropriate Personal Protective Equipment (PPE) should be worn at all times when handling product. Consult SDS for more information.

## Certificate of Compliance

Certificate of compliance will be supplied upon request and is included with each shipment

## The Infrastructure Innovators

[QuakeWrap.com](http://QuakeWrap.com)

**QuakeWrap, Inc.**  
**6840 S. Tucson Blvd.**  
**Tucson, AZ 85756**

**Toll Free (866) QUAKEWRAP [782-5397]**

QuakeWrap, Inc. warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current technical data sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. QUAKEWRAP, INC. SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES.