



# QuakeWrap® U41C

## Description

QuakeWrap® U41C is a high-strength unidirectional carbon fabric. The fabric is black and is impregnated in the field using QuakeBond™ 300SR Saturating Resin to form a carbon fiber reinforced polymer (CFRP) used to strengthen structural elements. The fabric weighs 41 oz/yd<sup>2</sup> (1390 g/m<sup>2</sup>) and the fibers are oriented primarily in the longitudinal (0°) direction.

## Uses

- Increased live load capacity in buildings, bridges, floors, roofs, etc.
- Seismic retrofit of structural elements such as columns, unreinforced masonry walls, etc.
- Repair of large diameter pipes to achieve strengthening and water-proofing.
- Repair of damaged structural components caused by aggressive environments, fire, vehicle impact, aging, etc.
- Changes in structural system: new openings in floors, removal of existing walls, etc.
- Correction of design or construction errors: misplaced reinforcing bars, insufficient structural depth.

## Advantages

- High-strength and lightweight fabric ideal for confined spaces.
- Used for flexure and shear strengthening as well as confinement.
- Fully compatible and excellent adhesion to QuakeBond™ resins.
- Non-corrosive.
- Versatile; can be wrapped around complex shapes.
- Light weight does not alter mass & dynamic loads on structure.
- Alkali resistant.
- Special manufacturing of the fabric makes it very stable & prevents fraying.

## Coverage

30 ft<sup>2</sup> per 1-gallon (0.7 m<sup>2</sup> per 1-liter) QuakeBond™ 300SR

## Packaging

- Rolls: 24 in x 50 yards (610 mm x 45m).
- This fabric can be easily cut in the field into narrower widths of various lengths.

## Shelf Life & Storage

Shelf life is unlimited in proper storage conditions. Store in a dry environment at 45°-95°F (7°-35°C).

## Limitations

Design calculations must be made and certified by an independent licensed professional engineer. System is a vapor barrier. Concrete should not be encapsulated in areas of freeze/thaw.

## Fiber & Laminate Properties

	US Units	SI Units
<b>Fiber Properties:</b>		
<b>Aerial Weight</b>	41 oz/yd <sup>2</sup>	1390 g/m <sup>2</sup>
<b>Tensile Strength</b>	725 ksi	5 GPa
<b>Tensile Modulus</b>	39,160 ksi	270 GPa
<b>Ultimate Elongation</b>	1.9%	1.9%
<b>Density</b>	0.065 lbs/in <sup>3</sup>	1.76 g/cm <sup>3</sup>
<b>Laminate with 300SR: *</b>		
<b>Tensile Strength**</b>	153 ksi	1,055 MPa
<b>Tensile Modulus</b>	14,530 ksi	100,100 MPa
<b>Ultimate Elongation**</b>	0.99%	0.99%
<b>Breaking Force**</b>	10,240 lb/in.	1800 N/mm
<b>Ply Thickness</b>	0.067 in.	1.7 mm

\*Results based on tests of single plies of fabrics saturated with 300SR

\*\*Mean ultimate value minus three (3) standard deviations

## Surface Preparation

Surface must be clean and sound; it can be dry or damp but must be free of standing water and frost. Remove dust, laitance, grease, curing compounds, disintegrated materials, and other bond inhibiting materials from the surface. Existing uneven surfaces must be filled with an appropriate repair mortar. The adhesive strength of the substrate must be verified after surface preparation by random pull-off testing (ACI 503R) at the discretion of the engineer. Minimum tensile strength of 200 psi (1.4 MPa) with substrate failure is required for bond-critical applications. Blast clean, shot-blast, scarify or use other approved mechanical means to clean the substrate surface. Any sharp edges (i.e. fins, form-marks, etc.) must be ground smooth and flush. Sharp edges must be rounded to a minimum radius of ¼ in. (19 mm). Apply QuakeBond™ 220UR onto the substrate with a trowel or spatula to a nominal thickness of 40 mil (1mm). A notched trowel may be used for this application.

## The Infrastructure Innovators

QuakeWrap.com

QuakeWrap, Inc.  
6840 S. Tucson Blvd.  
Tucson, AZ 85756

Toll Free (866) QUAKEWRAP [782-5397]

QuakeWrap, Inc. warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current technical data sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. QUAKEWRAP, INC. SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES.



# QuakeWrap<sup>®</sup> U41C

## Application

QuakeWrap<sup>®</sup> U41C fabric must be saturated using a saturation machine with QuakeBond<sup>™</sup> 300SR to ensure full impregnation; for more details, refer to the Product Data Sheet for 300SR.

Prior to mixing and applying QuakeBond<sup>™</sup> 300SR, saturation epoxy must be preconditioned to a temperature of 70-85°F (22-29°C). Epoxy Temperatures below 70 °F, might not achieve proper impregnation due to viscosity change. Apply saturated fabric to the substrate surface that has been coated with QuakeBond<sup>™</sup> 220UR. Using gloved hands or a putty knife, carefully remove any entrapped air bubbles under the fabric; a plastic laminating roller can be used for this purpose. If required, additional layers of saturated fabric can be directly applied on top of previous layers. Feather the edges of the fabric with QuakeBond<sup>™</sup> 220UR.

Installation of QuakeWrap<sup>®</sup> fabrics may only be performed by specially trained and approved contractors.

Fabric can be cut to appropriate length using a commercial quality heavy duty scissor. Dull or worn cutting tools can damage, weaken or fray the fiber; their use should be avoided.

## Cleanup

Dispose of waste in accordance with local disposal regulations. Cured materials can only be removed mechanically. See QuakeBond<sup>™</sup> 300SR and 220UR SDSs for more information on resin cleanup.

## Caution

QuakeWrap<sup>®</sup> U41C is non-reactive. Caution must be used when handling since a fine carbon dust may be present on the surface. Gloves must be worn to protect against skin irritation. Caution must also be used when cutting the fabric to protect against airborne carbon dust generated by the cutting procedure. Use of an appropriate, properly fitting NIOSH approved respirator is recommended.

## First Aid

Appropriate Personal Protective Equipment (PPE) should be worn at all times when handling product. Consult SDS for more information.

## Certificate of Compliance

Certificate of compliance are available upon request and included with each shipment.

## The Infrastructure Innovators

[QuakeWrap.com](http://QuakeWrap.com)

**QuakeWrap, Inc.**  
**6840 S. Tucson Blvd.**  
**Tucson, AZ 85756**

**Toll Free (866) QUAKEWRAP [782-5397]**

QuakeWrap, Inc. warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current technical data sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. QUAKEWRAP, INC. SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES.